

PRODUCT DATA SHEET

DUR-O-BOND_®

MB8000

Fiberglass Reinforced and Corrosion Resistant Compound

CHEMICAL FAMILY:

UNSATURATED POLYESTER RESIN

PRODUCT DESCRIPTION:

- **DUR-O-BOND MB8000** is a high strength polyester bonding compound engineered for bonding FRP parts and for gel coat back-up and radius / contour forming applications.
- Smooths sharp corners and transitions to reduce air voids.
- Low shrinkage and exotherm reduce print thru and allow higher quality finishes.
- Excellent adhesion and shear strength
- Fiberglass reinforcement for extra strength
- Has excellent resistance to corrosion and heat distortion

MB8000 Specifications		Catalyzation of MB8000				
Color	Grey	Catalyst % by Weight	1.5			
Odor	Strong Styrene Odor	Gel Time (min)	15-20			
Viscosity Average (Brookfield		Peak Exotherm Temp	~265°F			
RVDVII+Pro, 1 QT, TF, 78°F, 0.5RPM)	5,000,000 – 6,500,000 cP	Peak Exotherm Time	~ 30 min			
Density (lbs/gal)	~ 10.5	Note: The above catalyzation results were obtained using a 100 g sample at 25°C (77°F) Incubator Temperature: 78 °F; MEKP Catalys Syrgis MEKP-9 or equivalent.				
VOC (Ibs/gal)	2.14 [VOC lbs/gal post cure: 0 lbs]					
Shelf Life	3 months					

MEKP	Usage Guide	Quart Sing		Single (Gallon	5 gallons	
Recomn	nended Amount	Volume (mL)	Weight (g)	Volume (mL)	Weight (g)	Volume (mL)	Weight (g)
	1.5 %	16.27	17.86	65.08	71.44	325.40	357.21
		Volume	Weight	Volume	Weight	Volume	Weight
Recomn	nended Amount	(fl.oz)	(oz)	(fl.oz)	(oz)	(fl.oz)	(oz)
	1.5 %	0.55	0.63	2.20	2.52	11.00	12.60

DUR-O-BOND_®

 $\textbf{BETTER} \mathrel{\scriptstyle{\odot}} \textbf{STRONGER} \mathrel{\scriptstyle{\odot}} \textbf{FASTER}$

NOTICE: Read all precautionary labels, MSDS guidelines and product warnings before using. The information contained herein is correct to the best of our knowledge and is subject to revision without notice. The data contained in this product bulletin is made without guarantee or representation as to results. Since application variables are a major factor in product performance, this information should serve as a general guide only. We suggest that laboratory testing should be performed prior to the use of any product in the field. Durant makes no warranties, express or implied, and limits any liability for breach of warranty, negligence or otherwise to the purchase price of the material.