

STAT-A-FLEX Standard Dry Times (minutes)

Temperature (°F)	Pot Life w/ Bottle of Hardener (1)	Dry (1)	Pot Life w/ 1/2 Bottle of Hardener (2)	Dry (2)	Pot Life w/ 1 oz Accelerator & Full Bottle of Hardener (3)	Dry (3)
32	30	60	N/A	N/A	8	42
40	22	49	N/A	N/A	7	35
50	14	37	N/A	N/A	5.5	28
60	8.5	25	N/A	N/A	N/A	N/A
70	5.5	20	9	23	N/A	N/A
80	4	15	6.5	18	N/A	N/A
90	3	13	5	16	N/A	N/A