



112 RAILROAD ST., REVERE, MA 02151  
(800) 420-0021; (781) 289-1400; (781) 289-1405 (FAX)  
www.durantcorp.com

## STAT-A-FLEX PRODUCT DATA SHEET

**PRODUCT NAME:** STAT-A-FLEX TRAFFIC LOOP SEALER  
**CHEMICAL FAMILY:** UNSATURATED POLYESTER RESIN

### PHYSICAL PROPERTIES:

BOILING POINT: 293°F (Styrene)  
SPECIFIC GRAVITY: 1.25 +/- 0.15  
VAPOR PRESSURE: (mm Hg) 5.2 (Styrene)  
PERCENT VOLATILE BY WT : 18-22 %  
VAPOR DENSITY (AIR=1): 3.6 (Styrene)  
EVAPORATION RATE (Bu Ace=1): UK  
SOLUBILITY IN WATER: Negligible  
WEIGHT PER GALLON: Approx. 10.5 lbs  
SHORE D HARDNESS @ 24HRS: 73 +/- 5  
VISCOSITY: 104 KU  
GEL TIME (@ 77 ° F): 10 – 20 min. [ASTM C881]  
TACK FREE (@ 77 ° F): 15-25 min.  
CURING TIME (@ 77 ° F): 45-60 min.  
ELONGATION: 18 - 20 % [ASTM D638-96]  
TENSILE STRENGTH: > 1000 psi [ASTM D638-96]  
FLEXURAL STRENGTH: >1200 psi [ASTM D790]  
ADHESION  
Steel : 800 +/- 100 psi  
Portland Cement: 300psi [ASTM D3163-84]  
ABSORPTION 24 HOURS  
Water: 0.2% [ASTM D570]  
No. 3 Oil 0.02% [ASTM D570]  
Gasoline 0.04% [ASTM D570]  
Jet Fuel (Submersion No Dissolution) 0.06%  
3% NaCl 0.2%

### STAT-A-FLEX ADVANTAGES:

- Two part, component system, utilizing a liquid methyl ethyl ketone peroxide (MEKP) hardener.
- Bonds to all road surfaces
- Self leveling liquid / Pours fluidly
- Requires no special equipment, just mix and pour
- Cures in less than 20 minutes to produce a tough weather resistant seal
- Adjustable dry times regulated by amount of hardener (MEKP) added
- Totally encapsulates traffic detector loop wire
- Will not react with wire insulation
- Formulated to withstand stresses due to traffic vibrations
- Resistant to cracking caused by expansion and contraction due to temperature changes
- Resistant to most chemicals and solvents including road salts, acids, hydrocarbons, brake fluids, oils, gasoline and jet fuel
- Available in 1 Gal., 3.5 Gal., and 5 Gal. pails

### STAT-A-FLEX Application Instructions:

- For best results STAT-A-FLEX should be mixed with a powered mixer
- Mix for one minute, then pour in desired amount of hardener and mix for two minutes
- Pour STAT-A-FLEX into saw cut to be filled (It's that easy!)
- Hardener component amounts may be adjusted according to temperature
- An ACCELERATOR is also available for use in colder climates to further reduce drying time
- NOTE: Improper mixing may cause poor results

### STAT-A-FLEX Storage and Shelf Life:

- Best if stored at temperatures under 80 °F
- Shelf life of 12 months (unopened)